

# Estokote Grey

## Polymer Modified Cementitious Waterproofing Slurry & Protective Coating

### Description

**Estokote Grey** is a cement based two component polymer modified flexible waterproof coating. When used in reservoir or similar structure, it is able to accommodate the bending moment of the structure when it is filled with water. It fills and seals pores and voids of concrete or Masonry Surfaces to prevent water infiltration.

It is compatible to concrete. The bonding agent imparts excellent adhesion to concrete surfaces and forms part of the structure.

It is also supply in white colour, by the name of **Estokote White**, where the properties remain unchanged.

**Estokote Grey has been tested by SIRIM BHD, in accordance to BS 6920, on the suitability for contact with drinking water, BS 1881, on Water Absorption Test, and complied with the specification in this data sheet.**

### Uses

**Estokote Grey** is suitable and widely been used, it is recommended for -

- Potable water tanks, reservoirs and water treatment plant
- Basement, retaining wall and tunnels
- Planter boxes, terraces and balconies
- Swimming pools & R.C gutter
- Bathrooms and kitchens

### Advantages

- Easy to mix, apply & impermeable
- Breathable and allows transmission of water vapour from interior of building
- Non-toxicity requirement especially for potable water.
- Protection of concrete against the effects of CO<sub>2</sub>, de-icing salts and water penetration.
- Flexible thermal expansion similar to concrete.
- Sealing non-movement fine cracks or pores of all masonry.
- Non-corrosive to steel or ferrous metal

### Standards Compliance

- **ASTM D4541**
- **BS 1881 Part 122:1983**
- **BS 6920 Part 1:2000**

### Physical Properties

Pull-Off Strength, N/mm <sup>2</sup> ASTM D4541	0.5 – 1.0
Toxicity Test, BS 6920 Part 1:2000	Complied
Water Absorption, BS 1881 Part 122:1983	< 1.0%

### Application Instructions

#### Preparation

The surfaces, which are to receive **Estokote Grey** coating, must be free from oil, grease, wax, dirt or loosely adhering particles and sharp edges or any other form of foreign material, which might affect adhesion. The surface must be roughened.

Spalled and deeply disintegrated concrete should be removed to sound concrete and repaired with a suitable concrete repair mortar such as Estopatch MP or Estocrete WR.

Absorbent surfaces have to be thoroughly saturated with water prior to application of first coat of Estokote Grey. However, no loose standing water should be on the surface before application.

#### Mixing

Mix in a clean container by slowly adding the powder component to the liquid component and stirring with slow speed mixer for 2 - 4 minutes to avoid lump formation. Use mixture within 30 minutes.

#### DO NOT ADD WATER!

#### Application

Whilst the substrate is still damp from saturation, apply the first coat. Leave to harden for approximately 4-8 hours at temperatures above 20 °C before applying the second coat.

For slurry consistency, apply **Estokote Grey** with **Estokote Brush** to achieve the required coverage. Please contact Estop for details. Spray or trowel applications can be undertaken as necessary using the correct mixing ratio to obtain satisfactory consistency. Re-mixed the **Estokote Grey** material remained in mixing vessel for every application of **Estokote Grey**. Minimum two coats are recommended.

For floor application, to avoid risk of damage to the first coat, it is recommended that the second coat be applied before 24 hours. If the second coat is applied 12 hours or later, the first coat shall be slightly prewetted, preferably using a fine spray. After the second coat has been applied better finishing can be achieved by rubbing down with a soft, dry sponge.

#### Over Coating

Allow the coating as above to be harden for at least 3 days prior subsequence over coating work.

For over coating with non-cementitious materials, please refer to Denka Technical Department.

## Protection

The freshly applied waterproof coating shall be protected from rain, dirt, oil grease or other loose materials during its drying time.

The contractor should also take precautions to protect the **Estokote Grey** coating from any mechanical damage during the construction of other trade of works.

**Estokote Grey** waterproofing system to floors should be protected from damage by applying a protective screed.

## Installation of Wall Tiles on Estokote Grey

It is recommended to cure the **Estokote Grey** coating for 3 days before installation of wall tiles. Prior installation of wall tiles, the **Estokote Grey** coating shall be pre-wetted with water using a fine spray and sprinkled with OPC cement.

Apply the mixed tile adhesive or dry mixed mortar onto the saturated substrate with trowel. Level the tile adhesive to the desired thickness. Fix the tiles in position. Ensure the wall tiles are fully contacted with tile adhesive and avoid cavities formed.

Estokote Grey is designed as waterproofing system. Hence it is highly recommended that tile adhesive is used. If tile mortar is to be used, a low water (dry) mixture should be used **DO NOT USE TILE MORTAR THAT CONTAIN HIGH WATER**. Please contact Estop for details

## Curing

Precaution should be taken for applications done directly under sunlight and windy conditions. It should also be protected from direct rain for at least 4 hours.

The finishing coat shall be cured for 3-5 days before other trade shall be proceeded.

## Packing & Size

<b>Estokote Grey</b>	22.5 kg pack
<b>Estokote Long Brush</b>	11 inch
<b>Estokote Short Brush</b>	9 inch

## Coverage

<b>Estokote Grey</b>	11 m <sup>2</sup> per pack per two coats (2.1 kg/m <sup>2</sup> per two coats)
----------------------	---

## Technical Support

Denka offers a technical support package to specifiers, end-users and contractors, as well as on site technical assistance.

## Storage

**Estokote Grey** should be stored on pallets in dry conditions. Under these conditions the product will have a shelf life of 12 months.

## Precaution

**Estokote Grey** is non-toxic but is alkaline in nature. Gloves should be worn. Any splashes to the skin or eyes should be washed off immediately. In the event of prolonged irritation, seek medical advice.

## Additional Information

Denka Construction Solutions Malaysia Sdn Bhd and offers a wide range of complementary products which includes waterstops, waterproofing products, grouts, anchors, specialized flooring products. In addition, a wide range of products formulated for repair and refurbishment of spalled concrete are available.

**Denka Construction Solutions Malaysia Sdn Bhd**  
(Formerly known as Estop Sdn Bhd)

No. 18, Jalan Utas 15/7, Seksyen 15,  
40200 Shah Alam, Selangor Darul Ehsan, Malaysia  
Tel: +60 3 5510 8810 Fax: +60 3 5518 8202  
[www.denka-cs.com](http://www.denka-cs.com)

## Limitation of liability

*The information contained in this brochure provides general advice for potential customers of DENKA about the basic properties and characteristics of various DENKA products (hereafter referred to as "the Product Information"). DENKA makes no warranty or representation as to the entire accuracy or completeness of the Product Information in this brochure. Nothing in this brochure will be deemed to create any express or implied warranty of merchantability, fitness for a particular purpose, or infringement of any intellectual property rights. Each user of the Product Information and DENKA products assumes their own responsibility to properly determine the manner and suitability of use of the Product Information and DENKA products in its own operations. The user should exercise proper care in considering the Material Safety Data Sheet, Product Information and any other technical information provided by Denka including descriptions of the conditions of use, warnings, and other cautionary instructions. DENKA reserves the right to change the Product Information from time to time at its discretion and without notice.*